

Supplementary Tables

Table 1. Chemical composition of sample bodies (wt%).

Label	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃	TiO ₂	CaO	MgO	K ₂ O	Na ₂ O
HF-1	68.97	18.76	7.80	0.56	0.10	0.10	2.20	0.50
HF-2	67.66	20.67	6.84	0.82	0.06	0.49	2.43	0.04
HF-3	64.53	19.62	10.42	0.78	0.06	0.68	2.42	0.49
HF-4	63.94	21.37	9.21	0.71	0.06	0.56	2.80	0.36
HF-5	63.93	21.16	9.56	0.80	0.06	0.56	2.58	0.35
HF-6	66.53	20.78	8.34	0.61	0.06	0.44	2.20	0.04
HF-7	67.90	18.63	8.41	0.51	0.06	0.48	2.23	0.77
HF-8	64.30	23.67	6.70	0.71	0.08	0.57	2.66	0.30
HF-9	70.32	16.66	9.25	0.47	0.07	0.43	1.52	0.28
HF-10	69.92	20.28	5.30	0.40	0.06	0.49	2.51	0.03
HF-11	65.25	19.94	9.22	0.82	0.06	0.50	2.60	0.61
HF-12	65.36	17.33	11.46	0.58	0.06	0.85	2.82	0.55
HF-13	63.95	21.19	9.42	0.67	0.06	0.80	2.35	0.56
HF-14	68.51	18.94	7.25	0.77	0.07	0.81	2.12	0.53
HF-15	68.19	20.81	6.02	0.51	0.10	0.56	2.51	0.29
Mean	66.62	19.99	8.35	0.65	0.07	0.55	2.40	0.38
S.D.	2.22	1.69	1.64	0.13	0.02	0.18	0.31	0.22
OS-1	69.05	18.12	8.33	0.49	0.12	0.44	2.13	0.33
OS-2	66.47	21.06	7.04	0.63	0.12	0.74	2.91	0.04
OS3	66.63	19.28	9.27	0.64	0.14	0.57	2.44	0.03
OS-4	64.36	23.08	7.29	0.70	0.05	0.58	2.67	0.27
OS-5	62.60	23.13	9.20	0.62	0.05	0.78	2.37	0.24
OS-6	61.17	24.01	9.39	0.86	0.08	0.44	2.87	0.18
OS-7	64.73	20.66	8.68	0.56	0.09	1.02	2.42	0.86
OS-8	62.05	22.10	9.34	0.78	0.05	0.79	3.14	0.74
OS-9	64.03	21.57	9.31	0.79	0.06	0.53	2.37	0.33
OS-10	71.81	16.25	7.59	0.70	0.07	0.37	1.95	0.26
OS-11	67.05	20.13	7.80	0.68	0.05	0.48	2.45	0.37
OS-12	72.16	17.13	6.13	0.57	0.11	0.39	2.11	0.40
Mean	66.01	20.54	8.28	0.67	0.08	0.59	2.49	0.34
S.D.	3.43	2.36	1.05	0.10	0.03	0.19	0.34	0.24

Table 2. Chemical composition of sample glazes (wt%).

Label	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃	TiO ₂	CaO	MgO	K ₂ O	Na ₂ O	MnO	P ₂ O ₅
HF-1	63.76	17.10	5.99	0.50	6.29	1.22	3.69	0.46	0.38	0.25
HF-2	63.91	17.37	5.34	0.32	6.34	1.78	3.33	0.60	0.27	0.26
HF-3	64.34	17.48	5.72	0.40	5.27	1.64	3.49	0.65	0.23	0.13
HF-4	65.53	17.09	4.42	0.31	5.46	1.93	3.57	0.69	0.21	0.22
HF-5	64.00	16.32	5.80	0.28	6.09	2.28	3.64	0.57	0.32	0.25
HF-6	64.46	16.72	4.90	0.32	6.73	2.02	3.30	0.56	0.28	0.30
HF-7	64.73	17.62	5.09	0.36	5.72	1.65	3.40	0.43	0.40	0.32
HF-8	67.44	15.51	5.86	0.25	4.48	1.23	3.63	0.59	0.25	0.17
HF-9	63.87	18.26	4.90	0.33	6.21	2.16	3.12	0.15	0.28	0.27
HF-10	63.60	17.90	5.17	0.31	6.01	2.42	3.35	0.24	0.32	0.32
HF-11	66.36	15.96	4.20	0.29	5.62	2.08	3.62	0.87	0.27	0.25
HF-12	64.58	16.76	5.34	0.33	6.22	1.99	3.40	0.37	0.30	0.30
HF-13	64.63	16.31	5.29	0.32	6.25	2.38	3.31	0.50	0.29	0.28
HF-14	62.30	16.61	6.08	0.37	7.22	1.82	3.59	1.01	0.25	0.28
HF-15	65.91	17.56	4.53	0.33	5.65	1.33	3.41	0.27	0.30	0.22
Mean	64.63	16.97	5.24	0.34	5.97	1.86	3.46	0.53	0.29	0.25
S.D.	1.22	0.73	0.56	0.06	0.62	0.38	0.16	0.22	0.05	0.05
OS-1	70.46	13.72	3.70	0.26	4.51	1.72	4.29	0.33	0.26	0.10
OS-2	68.99	14.09	5.10	0.40	4.71	1.39	3.44	0.89	0.35	0.23
OS-3	69.46	14.28	4.52	0.32	5.30	1.08	3.62	0.42	0.30	0.15
OS-4	66.22	16.33	4.85	0.33	5.41	1.67	4.01	0.18	0.41	0.24
OS-5	66.55	16.05	5.56	0.40	4.70	0.97	4.23	0.55	0.59	0.41
OS-6	62.91	15.76	6.02	0.29	5.51	2.91	3.60	2.01	0.50	0.22
OS-7	67.12	15.83	4.67	0.30	5.29	1.59	4.00	0.20	0.32	0.25
OS-8	66.28	16.46	5.55	0.33	5.34	1.44	3.28	0.31	0.57	0.31
OS-9	67.87	14.60	3.83	0.37	4.95	1.95	4.04	1.40	0.36	0.21
OS-10	65.62	16.88	4.37	0.25	4.79	1.68	4.94	0.48	0.39	0.24
OS-11	68.69	14.62	5.71	0.38	4.33	0.65	4.24	0.39	0.42	0.22
OS-12	67.80	15.93	4.55	0.33	5.75	1.05	3.54	0.03	0.34	0.21
Mean	67.33	15.38	4.87	0.33	5.05	1.51	3.94	0.60	0.40	0.23
S.D.	1.93	1.01	0.71	0.05	0.43	0.55	0.44	0.55	0.10	0.07